



# BEARING DOCTOR

Diagnosis of bearing problems. Objective: Smooth & reliable operation.

**FV BEARING INDUSTRIES**  
**WWW.FV-BEARING.COM**

---

---

On the occasion of the “New Bearing Doctor” pamphlet being published, we would like to express our sincere thanks for your continuous patronage of FV products.

This pamphlet contains explanations about correct bearing handling, mounting, lubrication, and maintenance to prevent premature failure together with color photos of bearing failures.

Bearings become unserviceable when they suffer premature failure which is due to a lack of attention to proper han-

dling and/or maintenance.

This pamphlet is useful in determining causes of and measures against premature failure.

It's our pleasure to offer you this pamphlet.

Please be sure to consult the FV Rolling Bearing Catalog for more details regarding handling, maintenance, etc.

# Index of “ Bearing Doctor ”

Topic	Page
1. Introduction .....	3
2. Bearing Handling.....	4
2.1 Precautions for Handling.....	4
2.2 Mounting .....	4
2.3 Check the Operation .....	4
3. Bearing Maintenance.....	5
4. Bearing Performance Factors .....	5
4.1 Bearing Noise.....	5
4.2 Bearing Vibration.....	5
4.3 Bearing Temperature.....	5
4.4 Effects of Lubrication .....	5
4.5 Selection of Lubrication .....	6
4.6 Replenishment and Replacement of Lubricant.....	7
5. Bearing Inspection.....	7
6. Running Traces and Applied Loads .....	8
7. Bearing Damage and Measures.....	9
7.1 Flaking.....	10
7.2 Peeling .....	12
7.3 Scoring.....	13
7.4 Smearing.....	15
7.5 Fracture.....	17
7.6 Cracks.....	18
7.7 Cage Damage .....	20
7.8 Denting.....	22
7.9 Pitting.....	23
7.10 Wear .....	24
7.11 Fretting.....	25
7.12 False Brinelling.....	26
7.13 Creep .....	27
7.14 Seizure .....	28
7.15 Electrical Corrosion .....	29
7.16 Rust and Corrosion .....	30
7.17 Mounting Flaws.....	31
7.18 Discoloration .....	32
Appendix: Bearing Diagnostic Chart.....	33

# 1. Introduction

When a rolling bearing is damaged during machine operation, the entire machine or equipment may seize or malfunction. Since bearings that fail prematurely or unexpectedly cause trouble, it is important to be able to identify and predict failure beforehand, if possible, so that preventive measures can be adopted.

Generally, bearing inspection or housing inspection can identify the cause of the problem. Often the cause is attributable to poor lubrication, improper handling, selecting the wrong bearing, or not enough study of the shaft and

housing. Usually the cause can be determined by considering operation of the bearing before the failure, investigating the lubrication conditions and the mounting condition, and carefully observing the damaged bearing itself.

Sometimes bearings are damaged and fail both quickly and unexpectedly. Such premature failure is different from fatigue failure which is due to flaking. Bearing life can be separated and categorized into two types: premature failure and normal rolling contact fatigue.

# 2. Bearing Handling

## 2.1 Precautions for Handling

Since rolling bearings are high precision machine parts, they must be handled carefully. Even if high quality bearings are used, their expected life and performance cannot be attained if they are used improperly. The main precautions to be observed are as follows:

- (1) **Keep the Bearings and Surrounding Area Clean:** Dust and dirt, even if invisible to the naked eye, have harmful effects on bearings. It is necessary to prevent the entry of dust and dirt by keeping the bearings and their environment as clean as possible.
- (2) **Careful Handling:** Heavy shocks during handling may scratch or cause other damage to the bearing possibly resulting in bearing failure. Strong impacts may cause brinelling, breaking, or cracking.
- (3) **Use Proper Tools:** Always use the proper tool when handling bearings and avoid general purpose tools.
- (4) **Prevent Corrosion:** Since perspiration on the hands and various other contaminants may cause corrosion, keep your hands clean when handling bearings. Wear gloves if possible.

## 2.2 Mounting

It is advisable to study the bearing mounting thoroughly since the quality of the bearing mounting influences the bearing's running accuracy, life, and performance. It is recommended that the mounting method include the following steps.

- (1) Clean the bearing and surrounding parts.
- (2) Check the dimensions and finish conditions of related parts.
- (3) Follow mounting procedure.
- (4) Check if the bearing is mounted correctly.
- (5) Supply with correct kind and quantity of lubricant.

Since most bearings rotate with the shaft, the bearing mounting method is generally an interference (tight) fit for the inner ring and shaft while giving a clearance (loose) fit for the outer ring and housing.

## 2.3 Check the Operation

After mounting the bearing, it is important to carry out an operating test to confirm that the bearing is mounted properly. Table 2.1 indicates operating test methods. If irregularities are detected, immediately suspend the test and consult Table 2.2 which lists appropriate measures to specific bearing problems.

Table 2.1 Methods to check operation

Machine size	Operating procedure	Bearing condition checks
Small machine	Manual operation. Turn the bearing by hand. If no problems are detected, then proceed to operate the machine.	Stick-slip (Debris, cracks, dents). Uneven rotating torque (Faulty mounting). Excessive torque (Error in mounting or insufficient radial internal clearance).
	Power operation. Initially start at a low speed and without a load. Gradually increase speed and load to reach rating.	Check for irregular noise. Check for bearing temperature rise. Lubricant leakage. Discoloration.
Large machine	Idle operation. Turn ON power and allow machine to rotate slowly. Turn OFF the power and allow the bearing to coast to a stop. If no irregularities are detected by the test, then proceed to the loaded rotation testing.	Vibration. Noise, etc.
	Power operation. Follow the same power operation testing as used for small machine testing.	Follow the same checkpoints as the small machine test.

Table 2.2 Causes and measures for operating irregularities

Irregularities		Possible causes	Measures
Noise	Loud Metallic Sound	Abnormal load	Improve the fit, internal clearance, preload, position of housing shoulder, etc.
		Incorrect mounting	Improve the machining accuracy and alignment of shaft and housing, accuracy of mounting method.
		Insufficient or improper lubricant	Replenish the lubricant or select another lubricant.
	Loud Regular Sound	Contact of rotating parts	Modify the labyrinth seal, etc.
		Flaws, corrosion, or scratches on raceways	Replace or clean the bearing, improve the seals, and use clean lubricant.
		Brinelling	Replace the bearing and use care when handling bearings.
Irregular Sound	Flaking on raceway	Replace the bearing.	
	Excessive clearance	Improve the fit, clearance and preload.	
	Penetration of foreign particles	Replace or clean the bearing, improve the seals, and use clean lubricant.	
Abnormal Temperature Rise	Flaws or flaking on balls	Replace the bearing.	
	Excessive amount of lubricant	Reduce amount of lubricant, select stiffer grease.	
	Insufficient or improper lubricant	Replenish lubricant or select a better one.	
	Abnormal load	Improve the fit, internal clearance, preload, position of housing shoulder.	
	Incorrect mounting	Improve the machining accuracy and alignment of shaft and housing, accuracy of mounting, or mounting method.	
Vibration (Axial runout)	Creep on fitted surface, excessive seal friction	Correct the seals, replace the bearing, correct the fitting or mounting.	
	Brinelling	Replace the bearing and use care when handling bearings.	
	Flaking	Replace the bearing.	
	Incorrect mounting	Correct the squareness between the shaft and housing shoulder or side of spacer.	
Leakage or Discoloration of Lubricant	Penetration of foreign particles	Replace or clean the bearing, improve the seals.	
	Too much lubricant, Penetration by foreign matter or abrasion chips.	Reduce the amount of lubricant, select a stiffer grease. Replace the bearing or lubricant. Clean the housing and adjacent parts.	

### 3. Bearing Maintenance

It is necessary to periodically inspect and maintain the bearing and its operating conditions in order to maximize the bearing life. In general, the following method is adopted.

**(1) Inspection under operating conditions**

To determine the bearing replacement periods and replenishment intervals for lubricant, investigate the lubricant properties and consider factors such as operating temperature, vibration, and bearing noise. (Refer to Section 4 for more details.)

**(2) Inspection of the bearing**

Be sure to investigate the bearing thoroughly during times of periodic machine inspection and part replacement. Check the raceway condition. Determine if damage exists. Confirm if the bearing can be reused or should be replaced. (Refer to Section 5 for more details.)

### 4. Bearing Performance Factors

Key bearing performance factors during operation are bearing noise, vibration, temperature, and lubricant state. Please refer to Table 2.2 if any operation irregularities are detected.

**4.1 Bearing Noise**

During operation, sound detection instruments (stethoscope, FV Bearing Industries, etc.) can be used to investigate the volume and characteristics of the bearing rotation noise. It is possible to distinguish bearing damage such as small flaking by means of its unusual yet characteristic noise.

**4.2 Bearing Vibration**

Bearing irregularities can be analyzed by measuring the vibrations of an operating machine. A frequency spectrum analyzer is used to measure the magnitude of vibration and the distribution of the frequencies. Test results enable the determination of the likely cause of the bearing irregularity. The measured data varies depending on the operating conditions of the bearing and the location of the vibration pick-up. Therefore, the method requires the determination of evaluation standards for each measured machine.

It is useful to be able to detect irregularities from the bearing vibration pattern during operation. Please refer to the FV pamphlet CAT. No. E410 (Bearing Monitor) for more information about such a device.

**4.3 Bearing Temperature**

Generally, the bearing temperature can be estimated from the temperature of the housing outside surface, but a preferable way is to obtain direct measurements from the bearing outer ring by a probe going through an oil hole.

Usually, the bearing temperature gradually increases after the start of operation until reaching a steady state condition about 1 or 2 hours later. The bearing steady state temperature depends on load, rotational speed and heat transfer properties of the machine. Insufficient lubrication or improper mounting might cause the bearing temperature to rise rapidly. In such a case, suspend the machine operation and adopt an appropriate countermeasure.

**4.4 Effects of Lubrication**

The two main purposes of lubrication are to minimize friction and reduce wear inside bearings that might otherwise fail prematurely. Lubrication provides the following advantages:

**(1) Reduction of Friction and Wear**

Direct metallic contact between the bearing rings, rolling elements and cage, which are the basic components of a bearing, is prevented by an oil film which reduces the friction

and wear in the contact areas.

**(2) Extension of Fatigue Life**

The rolling fatigue life of bearings depends greatly upon the viscosity and film thickness between the rolling contact surfaces. A heavy film thickness prolongs the fatigue life, but it is shortened if the viscosity of the oil is too low so that the film thickness is insufficient.

**(3) Dissipation of Frictional Heat and Cooling**

Circulation lubrication may be used to carry away either frictional heat or heat transferred from the outside to prevent the bearing from overheating and the oil from deteriorating.

**(4) Sealing and Rust Prevention**

Adequate lubrication also helps to prevent foreign material from entering the bearings and guards against corrosion or rusting.

**4.5 Selection of Lubrication**

Bearing lubrication methods are divided into two main categories: grease lubrication and oil lubrication. A lubrication method is adopted that matches the application conditions and application purpose in order to attain best performance from the bearing. Table 4.1 shows a comparison between grease and oil lubrication.

**Table 4.1** Comparison between grease and oil lubrication

Item	Grease lubrication	Oil lubrication
Housing structure and seal method	Simple	May be complex. Careful maintenance required.
Speed	Limiting speed is 65% to 80% of that with oil lubrication	High limiting speed
Cooling effect	Poor	Heat transfer is possible using forced oil circulation
Fluidity	Poor	Good
Lubricant replacement	Sometimes difficult	Easy
Removal of foreign material	Removal of particles from grease is impossible	Easy
External contamination due to leakage	Surroundings seldom contaminated by leakage	Often leaks if proper countermeasures are not taken. Not suitable if external contamination must be avoided.

**(1) Grease Lubrication**

Grease is a lubricant that is made from base oil, thickener, and additives. When selecting a grease, it is necessary to select a grease that is suitable to the bearing application conditions. There are large differences in performance even between different brands of the same type of grease. Therefore special attention must be given to grease selection. Table 4.2 gives examples of applications and grease consistency.

**(2) Oil Lubrication**

There are several different oil lubrication methods: Oil bath, Drip feed, Splash, Circulating, Jet, Oil mist, and Oil air. Oil lubrication methods are more suitable for higher speed and higher temperature applications than are grease lubrication methods. Oil lubrication is especially effective in the case where it is necessary to dissipate heat to the exterior.


Be sure to select a lubricating oil that has suitable viscosity at the bearing operating temperature. Generally, an oil with a low viscosity is used for high speed application while an oil with high viscosity is used for applications with heavy loads. For normal application conditions, Table 4.3 lists the suitable viscosity range for the operating temperature.

For reference when making a selection, Fig. 4.1 shows the relationship between temperature and viscosity for the lubricating oil. Table 4.4 gives examples of how to select the lubrication oil for different bearing application conditions.

**Table 4.3** Required viscosity by bearing type

Bearing type	Viscosity at operating temperature
Ball bearings, Cylindrical roller bearings	13 mm <sup>2</sup> /s or more
Tapered roller bearings, Spherical roller bearings	20 mm <sup>2</sup> /s or more
Spherical thrust roller bearings	32 mm <sup>2</sup> /s or more

Remarks: 1 mm<sup>2</sup>/s = 1 cSt (Centi-Stokes)



**Fig. 4.1** Relation between oil viscosity and temperature

**Table 4.2** Examples of applications and grease consistency

Consistency number	# 0	# 1	# 2	# 3	# 4
Consistency (1/10 mm)	355 to 385	310 to 340	265 to 295	220 to 250	175 to 205
Application	Central grease supply	Central grease supply, Low temperature	General grease	General grease, High temperature	High temperature
	Where fretting occurs easily	Where fretting occurs easily	Sealed ball bearings	Sealed ball bearings	Where grease is used as a seal

**Table 4.4** Selection of lubricating oils for different bearing applications

Operating temperature	Speed	Light or normal load	Heavy or shock load
-30 to 0°C	Below limiting speed	ISO VG 15, 22, 32 (Refrigerator oil)	—
0 to 50°C	Below 50% of limiting speed	ISO VG 32, 46, 68 (Bearing oil, Turbine oil)	ISO VG 46, 68, 100 (Bearing oil, Turbine oil)
	Between 50% and 100% of limiting speed	ISO VG 15, 22, 32 (Bearing oil, Turbine oil)	ISO VG 22, 32, 46 (Bearing oil, Turbine oil)
	Above limiting speed	ISO VG 10, 15, 22 (Bearing oil)	—
50 to 80°C	Below 50% of limiting speed	ISO VG 100, 150, 220 (Bearing oil)	ISO VG 150, 220, 320 (Bearing oil)
	Between 50% and 100% of limiting speed	ISO VG 46, 68, 100 (Bearing oil, Turbine oil)	ISO VG 68, 100, 150 (Bearing oil, Turbine oil)
80 to 110°C	Above limiting speed	ISO VG 32, 46, 68 (Bearing oil, Turbine oil)	—
	Below 50% of limiting speed	ISO VG 320, 460 (Bearing oil)	ISO VG 460, 680 (Bearing oil, Gear oil)
	Between 50% and 100% of limiting speed	ISO VG 150, 220 (Bearing oil)	ISO VG 220, 320 (Bearing oil)
80 to 110°C	Above limiting speed	ISO VG 68, 100 (Bearing oil, Turbine oil)	—

Notes: 1. As for the limiting speed, use the value listed under oil lubrication in the Bearing Dimension Tables of "FV Rolling Bearings".  
 2. Refer to refrigerator oil (JIS K 2211), Bearing oil (JIS K 2239), Turbine oil (JIS K 2213), Gear oil (JIS K 2219).  
 3. Temperature ranges are shown in the left column in the table above. For operating temperatures that are on the high temperature side, a high viscosity lubrication oil is recommended.



#### 4.6 Replenishment and Replacement of Lubricant

##### (1) Replenishing Interval

Even if high-quality grease is used, there is deterioration of its properties with time; therefore, periodic replenishment is required. Figs. 4.2 (1) and (2) show the replenishment time intervals for various bearing types running at different speeds. Figs. 4.2 (1) and (2) apply for the condition of high-quality lithium soap-mineral oil grease, bearing temperature of 70°C, and normal load ( $P/C=0.1$ ).

##### • Temperature

If the bearing temperature exceeds 70°C, the replenishment time interval must be reduced by half for every 15°C temperature rise of the bearings.

##### • Grease

In case of ball bearings especially, the replenishing time interval can be extended depending on used grease type. (For example, high-quality lithium soap-synthetic oil grease may extend about two times of replenishing time interval shown in Fig. 4.2 (1). If the temperature of the bearings is less

than 70°C, the usage of lithium soap-mineral oil grease or lithium soap-synthetic oil grease is appropriate.) It is advisable to consult FV.

##### • Load

The replenishing time interval depends on the magnitude of the bearing load.

Please refer to Fig. 4.2 (3), and multiply the replenishing time interval by the load factor.

If  $P/C$  exceeds 0.16, it is advisable to consult FV.

##### (2) Lubrication oil replacement interval

The oil replacement intervals depend on the operating conditions and the oil quantity. In general, for an operating temperature under 50°C, and in clean environments, the replacement interval is 1 year. If the oil temperature is above 100°C, then the oil should be changed at least once every three months.

Remarks  $P$ : Equivalent load  
 $C$ : Basic load rating




Fig. 4.2 Grease replenishment intervals

## 5. Bearing Inspection

When inspecting a bearing during periodic inspection of equipment, operating inspections, or replacement of adjacent parts, determine the condition of the bearing and if its continued service is advisable.

A record should be kept of the inspection and external appearance of dismounted bearings. After taking a grease sample and measuring the quantity of residual grease, the bearing should be cleaned. Also, determine whether abnormalities and damage exist in the cage, fitting surfaces, rolling element surfaces, and raceway surfaces. Refer to Section 6 regarding the observation of running traces on the raceway surface.

When evaluating whether a bearing can be reused or not, the following points need to be considered: degree of bearing damage, machine performance, critical nature of the application, operating conditions, inspection interval. If the inspection reveals bearing damage or abnormalities, then try to confirm the cause and determine a measure by referring to Section 7 and then carry out the countermeasure.

If your inspection discovers any of the following kinds of damage, which would prevent the bearing from being reused, then the bearing must be replaced with a new one.

- (1) Cracks or chipping in the cage, rolling elements, or raceway ring.
- (2) Flaking in the rolling elements or raceway ring.
- (3) Notable scoring on the rolling elements, rib face (collar), or raceway surface.
- (4) Notable wear on the cage or loose rivets.
- (5) Flaws or rust on the rolling elements or raceway surface.
- (6) Notable dents on the rolling elements or raceway surface.
- (7) Notable creep of the outer ring outside surface or inner ring bore.
- (8) Discoloration due to heating.
- (9) Serious damage on shield or seal of grease packed bearings.

## 6. Running Traces and Applied Loads

As the bearing rotates, the raceways of the inner ring and outer ring make contact with the rolling elements. This results in a wear path on both the rolling elements and raceways. Running traces are useful, since they indicate the loading conditions, and should be carefully observed when the bearing is disassembled.

If the running traces are clearly defined, it is possible to determine whether the bearing is carrying a radial load, axial load or moment load. Also, the roundness condition of the bearing can be determined. Check whether unexpected bearing loads or large mounting errors occurred. Also, determine the probable cause of the bearing damage.

Fig. 6.1 shows the running traces generated in deep groove bearings under various load conditions. Fig. 6.1 (a) shows the most common running trace generated when the inner ring rotates under a radial load only. Figs. 6.1 (e) through (h) show several different running traces that result in a shortened life due to their adverse effect on the bearings.

Similarly, Fig. 6.2 shows different roller bearing running traces: Fig. 6.2 (i) shows the outer ring running trace when a radial load is properly applied to a cylindrical roller bearing which has a load on a rotating inner ring. Fig. 6.2 (j) shows the running trace in the case of shaft bending or relative inclination between the inner and outer rings. This misalignment leads to the generation of slightly shaded (dull) bands in the width direction. Traces are diagonal at the beginning and end of the loading zone. For double-row tapered roller bearings where a single load is applied to the rotating inner ring, Fig. 6.2 (k) shows the running trace on the outer ring under radial load while Fig. 6.2 (l) shows the running trace on the outer ring under axial load. When misalignment exists between the inner and the outer rings, then the application of a radial load causes running traces to appear on the outer ring as shown in Fig. 6.2 (m).




Fig. 6.1 Typical running traces of deep groove ball bearings




Fig. 6.2 Typical running traces on roller bearings

## 7. Bearing Damage and Measures

In general, if rolling bearings are used correctly, they will survive to their predicted fatigue life. Bearings, however, often fail prematurely due to avoidable mistakes. In contrast to fatigue life, this premature failure is caused by improper mounting, mishandling, poor lubrication, entry of foreign matter or abnormal heat generation.

For example, one cause of premature failure is rib scoring which is due to insufficient lubrication, use of improper lubricant, faulty lubrication system, entry of foreign matter, bearing mounting error, excessive deflection of the shaft or some combination of these. If all conditions are known for the times

both before and after the failure, including the application, the operating conditions, and environment, then a measure can be determined by studying the nature of the failure and its probable causes. A successful measure will reduce similar failures or prevent them from happening again.

Sections 7.1 through 7.18 give various type of bearing damage and measures. Please consult these sections when trying to determine the cause of bearing damage. By the way, the bearing diagnostic chart in the Appendix may be useful as a quick reference guide.

### 7.1 Flaking

Damage Condition	Possible Cause	Measures
Flaking occurs when small pieces of bearing material are split off from the smooth surface of the raceway or rolling elements due to rolling fatigue, thereby creating regions having rough and coarse texture.	Excessive load Poor mounting (misalignment) Moment load Entry of foreign debris, water penetration Poor lubrication, Improper lubricant Unsuitable bearing clearance Improper precision for shaft or housing, unevenness in housing rigidity, large shaft bending Progression from rust, corrosion pits, smearing, dents (Brinelling)	<ul style="list-style-type: none"> <li>Reconfirm the bearing application and check the load conditions</li> <li>Improve the mounting method</li> <li>Improve the sealing mechanism, prevent rusting during non-running</li> <li>Use a lubricant with a proper viscosity, improve the lubrication method</li> <li>Check the precision of shaft and housing</li> <li>Check the bearing internal clearance</li> </ul>



Photo 7-1-1

**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Flaking occurs around half of the circumference of the raceway surface  
**Cause:** Poor lubrication due to entry of cutting coolant into bearing



Photo 7-1-2

**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Flaking occurs diagonally along raceway  
**Cause:** Poor alignment between shaft and housing during mounting



Photo 7-1-3

**Part:** Inner ring of deep groove ball bearing  
**Symptom:** Flaking of raceway at ball pitch  
**Cause:** Dents due to shock load during mounting



Photo 7-1-4

**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Flaking of raceway at ball pitch  
**Cause:** Dents due to shock load while stationary




**Photo 7-1-5**  
**Part:** Outer ring of Photo 7-1-4  
**Symptom:** Flaking of raceway surface at ball pitch  
**Cause:** Dents due to shock load while stationary



**Photo 7-1-6**  
**Part:** Balls of Photo 7-1-4  
**Symptom:** Flaking of ball surface  
**Cause:** Dents due to shock load while stationary



**Photo 7-1-7**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Flaking of only one raceway over its entire circumference  
**Cause:** Excessive axial load



**Photo 7-1-8**  
**Part:** Outer ring of Photo 7-1-7  
**Symptom:** Flaking of only one raceway over its entire circumference  
**Cause:** Excessive axial load




**Photo 7-1-9**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Flaking of only one row of raceway  
**Cause:** Poor lubrication



**Photo 7-1-10**  
**Part:** Rollers of a cylindrical roller bearing  
**Symptom:** Premature flaking occurs axially on the rolling surfaces  
**Cause:** Scratches caused during improper mounting

## 7.2 Peeling

Damage Condition	Possible Cause	Measures
Dull or cloudy spots appear on surface along with light wear. From such dull spots, tiny cracks are generated downward to a depth of 5 to 10 μm. Small particles fall off and minor flaking occurs widely.	Unsuitable lubricant Entry of debris into lubricant Rough surface due to poor lubrication Surface roughness of mating rolling part	<ul style="list-style-type: none"> <li>Select a proper lubricant</li> <li>Improve the sealing mechanism</li> <li>Improve the surface finish of the rolling mating parts</li> </ul>



**Photo 7-2-1**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Round shaped peeling pattern occurs on the center of the raceway surface  
**Cause:** Poor lubrication



**Photo 7-2-2**  
**Part:** Enlargement of pattern in Photo 7-2-1



**Photo 7-2-3**  
**Part:** Convex rollers of Photo 7-2-1  
**Symptom:** Round shaped peeling pattern occurs on the center of the rolling surfaces  
**Cause:** Poor lubrication



**Photo 7-2-4**  
**Part:** Outer ring of a spherical roller bearing  
**Symptom:** Peeling occurs near the shoulder of the raceway over the entire circumference  
**Cause:** Poor lubrication



### 7.3 Scoring

Damage Condition	Possible Cause	Measures
Scoring is surface damage due to accumulated small seizures caused by sliding under improper lubrication or under severe operating conditions. Linear damage appears circumferentially on the raceway surface and rolling surface. Linear damage appears circumferentially on the raceway surface and rolling surface. Cycloidal shaped damage on the roller end. Scoring on rib surface contacting roller end.	Excessive load, excessive preload Poor lubrication Particles are caught in the surface Inclination of inner and outer rings Shaft bending Poor precision of the shaft and housing	<ul style="list-style-type: none"> <li>• Check the size of the load</li> <li>• Adjust the preload</li> <li>• Improve the lubricant and the lubrication method</li> <li>• Check the precision of the shaft and housing</li> </ul>



**Photo 7-3-5**  
**Part:** Inner ring of a spherical thrust roller bearing  
**Symptom:** Scoring on the rib face of inner ring  
**Cause:** Debris, which is caught in surface, and excessive axial loading




**Photo 7-3-6**  
**Part:** Convex rollers of Photo 7-3-5  
**Symptom:** Scoring on the roller end face  
**Cause:** Debris, which is caught in surface, and excessive axial loading




**Photo 7-3-1**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Scoring on large rib face of inner ring  
**Cause:** Roller slipping due to sudden acceleration and deceleration



**Photo 7-3-2**  
**Part:** Convex rollers of Photo 7-3-1  
**Symptom:** Scoring on roller end face  
**Cause:** Roller slipping due to sudden acceleration and deceleration



**Photo 7-3-7**  
**Part:** Cage of a deep groove ball bearing  
**Symptom:** Scoring on the pressed-steel cage pockets  
**Cause:** Entry of debris




**Photo 7-3-3**  
**Part:** Inner ring of a tapered roller thrust bearing  
**Symptom:** Scoring on the face of inner ring rib  
**Cause:** Worn particles become mixed with lubricant, and breakdown of oil film occurs due to excessive load




**Photo 7-3-4**  
**Part:** Rollers of a double-row cylindrical roller bearing  
**Symptom:** Scoring on the roller end face  
**Cause:** Poor lubrication and excessive axial load

### 7.4 Smearing

Damage Condition	Possible Cause	Measures
Smearing is surface damage which occurs from a collection of small seizures between bearing components caused by oil film rupture and/or sliding. Surface roughening occurs along with melting.	High speed and light load Sudden acceleration/deceleration Improper lubricant Entry of water	<ul style="list-style-type: none"> <li>• Improve the preload</li> <li>• Improve the bearing clearance</li> <li>• Use a lubricant with good oil film formation ability</li> <li>• Improve the lubrication method</li> <li>• Improve the sealing mechanism</li> </ul>




**Photo 7-4-5**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Partial smearing occurs circumferentially on raceway surface  
**Cause:** Poor lubrication



**Photo 7-4-6**  
**Part:** Outer ring of Photo 7-4-5  
**Symptom:** Partial smearing occurs circumferentially on raceway surface  
**Cause:** Poor lubrication



**Photo 7-4-1**  
**Part:** Inner ring of a cylindrical roller bearing  
**Symptom:** Smearing occurs circumferentially on raceway surface  
**Cause:** Roller slipping due to excessive grease filling



**Photo 7-4-2**  
**Part:** Outer ring of Photo 7-4-1  
**Symptom:** Smearing occurs circumferentially on raceway surface  
**Cause:** Roller slipping due to excessive grease filling



**Photo 7-4-7**  
**Part:** Convex rollers of Photo 7-4-5  
**Symptom:** Smearing occurs at the center of the rolling surface  
**Cause:** Poor lubrication



**Photo 7-4-3**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Smearing occurs circumferentially on raceway surface  
**Cause:** Poor lubrication



**Photo 7-4-4**  
**Part:** Outer ring of Photo 7-4-3  
**Symptom:** Smearing occurs circumferentially on raceway surface  
**Cause:** Poor lubrication

### 7.5 Fracture


Damage Condition	Possible Cause	Measures
Fracture refers to small pieces which were broken off due to excessive load or shock load acting locally on a part of the roller corner or rib of a raceway ring.	Impact during mounting Excessive load Poor handling such as dropping	<ul style="list-style-type: none"> <li>• Improve the mounting method (Shrink fit, use of proper tools)</li> <li>• Reconsider the loading conditions</li> <li>• Provide enough back-up and support for the bearing rib</li> </ul>

### 7.6 Cracks


Damage Condition	Possible Cause	Measures
Cracks in the raceway ring and rolling elements. Continued use under this condition leads to larger cracks or fractures.	Excessive interference Excessive load, shock load Progression of flaking Heat generation and fretting caused by contact between mounting parts and raceway ring Heat generation due to creep Poor taper angle of tapered shaft Poor cylindricality of shaft Interference with bearing chamfer due to a large shaft corner radius	<ul style="list-style-type: none"> <li>• Correct the interference</li> <li>• Check the load conditions</li> <li>• Improve the mounting method</li> <li>• Use an appropriate shaft shape</li> </ul>



**Photo 7-5-1**  
**Part:** Inner ring of a double-row cylindrical roller bearing  
**Symptom:** Chipping occurs at the center rib  
**Cause:** Excessive load during mounting




**Photo 7-5-2**  
**Part:** Inner ring of a tapered roller bearing  
**Symptom:** Fracture occurs at the cone back face rib  
**Cause:** Large shock during mounting



**Photo 7-6-1**  
**Part:** Outer ring of a double-row cylindrical roller bearing  
**Symptom:** Thermal cracks occur on the outer ring side face  
**Cause:** Abnormal heat generation due to contact sliding between mating part and face of outer ring



**Photo 7-6-2**  
**Part:** Roller of a tapered roller thrust bearing  
**Symptom:** Thermal cracks occur at large end face of roller  
**Cause:** Heat generation due to sliding with the inner ring rib under poor lubrication



**Photo 7-5-3**  
**Part:** Inner ring of a spherical thrust roller bearing  
**Symptom:** Fracture occurs at the large rib  
**Cause:** Repeated load




**Photo 7-5-4**  
**Part:** Outer ring of a solid type needle roller bearing  
**Symptom:** Fracture occurs at the outer ring rib  
**Cause:** Roller inclination due to excessive loading (Needle rollers are long compared to their diameter. Under excessive or uneven loading, rollers become inclined and push against the ribs.)



**Photo 7-6-3**  
**Part:** Outer ring of a double-row cylindrical roller bearing  
**Symptom:** Cracks propagated outward in the axial and circumferential directions from the flaking origin on the raceway surface  
**Cause:** Flaking from a flaw due to shock



**Photo 7-6-4**  
**Part:** Outer ring of a double-row cylindrical roller bearing used for outer ring rolling (Outer ring rotation)  
**Symptom:** Cracks occur on outside surface  
**Cause:** Flat wear and heat generation due to non-rotation of the outer ring




**Photo 7-6-5**  
**Part:** Raceway surface of outer ring in Photo 7-6-4  
**Symptom:** Outside surface crack developing on the raceway



**Photo 7-6-6**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Axial cracks occur on raceway surface  
**Cause:** Large fitting stress due to temperature difference between shaft and inner ring.



**Photo 7-6-7**  
**Part:** Cross section of a fractured inner ring in Photo 7-6-6  
**Symptom:** Origin is directly beneath the raceway surface



**Photo 7-6-8**  
**Part:** Roller of a spherical roller bearing  
**Symptom:** Axial cracks occur on rolling surface

### 7.7 Cage Damage


Damage Condition	Possible Cause	Measures
Cage damage includes cage deformation, fracture, and wear Fracture of cage pillar Deformation of side face Wear of pocket surface Wear of guide surface	Poor mounting (Bearing misalignment) Poor handling Large moment load Shock and large vibration Excessive rotation speed, sudden acceleration and deceleration Poor lubrication Temperature rise	<ul style="list-style-type: none"> <li>• Check the mounting method</li> <li>• Check the temperature, rotation, and load conditions</li> <li>• Reduce the vibration</li> <li>• Select a cage type</li> <li>• Select a lubrication method and lubricant</li> </ul>



**Photo 7-7-1**  
**Part:** Cage of a deep groove ball bearing  
**Symptom:** Fracture of pressed-steel cage-pocket



**Photo 7-7-2**  
**Part:** Cage of an angular contact ball bearing  
**Symptom:** Pocket pillar fractures from a cast iron machined cage  
**Cause:** Abnormal load action on cage due to misaligned mounting between inner and outer rings



**Photo 7-7-3**  
**Part:** Cage of an angular contact ball bearing  
**Symptom:** Fracture of machined high-tension brass cage



**Photo 7-7-4**  
**Part:** Cage of a tapered roller bearing  
**Symptom:** Pillar fractures of pressed-steel cage






**Photo 7-7-5**  
**Part:** Cage of an angular contact ball bearing  
**Symptom:** Pressed-steel cage deformation  
**Cause:** Shock load due to poor handling



**Photo 7-7-6**  
**Part:** Cage of a cylindrical roller bearing  
**Symptom:** Deformation of the side face of a machined high-tension brass cage  
**Cause:** Large shock during mounting



**Photo 7-7-7**  
**Part:** Cage of a cylindrical roller bearing  
**Symptom:** Deformation and wear of a machined high-tension brass cage



**Photo 7-7-8**  
**Part:** Cage of an angular contact ball bearing  
**Symptom:** Stepped wear on the outside surface and pocket surface of a machined high-tension brass cage

### 7.8 Denting


Damage Condition	Possible Cause	Measures
When debris such as small metallic particles are caught in the rolling contact zone, denting occurs on the raceway surface or rolling element surface. Denting can occur at the rolling element pitch interval if there is a shock during the mounting (Brinell dents).	Debris such as metallic particles are caught in the surface Excessive load Shock during transport or mounting	<ul style="list-style-type: none"> <li>Wash the housing</li> <li>Improve the sealing mechanism</li> <li>Filter the lubrication oil</li> <li>Improve the mounting and handling methods</li> </ul>



**Photo 7-8-1**  
**Part:** Inner ring of a double-row tapered roller bearing  
**Symptom:** Frosted raceway surface  
**Cause:** Debris caught in the surface



**Photo 7-8-2**  
**Part:** Outer ring of a double-row tapered roller bearing  
**Symptom:** Indentations on raceway surface  
**Cause:** Debris caught in the surface



**Photo 7-8-3**  
**Part:** Inner ring of a tapered roller bearing  
**Symptom:** Small and large indentations occur over entire raceway surface  
**Cause:** Debris caught in the surface



**Photo 7-8-4**  
**Part:** Tapered rollers of Photo 7-8-3  
**Symptom:** Small and large indentations occur over the rolling surface  
**Cause:** Debris caught in the surface



### 7.9 Pitting

Damage Condition	Possible Cause	Measures
The pitted surface has a dull luster which appears on the rolling element surface or raceway surface.	Debris becomes caught in the lubricant Exposure to moisture in the atmosphere Poor lubrication	<ul style="list-style-type: none"> <li>• Improve the sealing mechanism</li> <li>• Filter the lubrication oil thoroughly</li> <li>• Use a proper lubricant</li> </ul>



**Photo 7-9-1**  
**Part:** Outer ring of a slewing bearing  
**Symptom:** Pitting occurs on the raceway surface  
**Cause:** Rust at bottoms of indentations



**Photo 7-9-2**  
**Part:** Ball of Photo 7-9-1  
**Symptom:** Pitting occurs on the rolling element surface

### 7.10 Wear

Damage Condition	Possible Cause	Measures
Wear is surface deterioration due to sliding friction at the surface of the raceway, rolling elements, roller end faces, rib face, cage pockets, etc.	Entry of debris Progression from rust and electrical corrosion Poor lubrication Sliding due to irregular motion of rolling elements	<ul style="list-style-type: none"> <li>• Improve the sealing mechanism</li> <li>• Clean the housing</li> <li>• Filter the lubrication oil thoroughly</li> <li>• Check the lubricant and lubrication method</li> <li>• Prevent misalignment</li> </ul>



**Photo 7-10-1**  
**Part:** Inner ring of a cylindrical roller bearing  
**Symptom:** Many pits occur due to electrical corrosion and wave-shaped wear on raceway surface  
**Cause:** Electrical corrosion



**Photo 7-10-2**  
**Part:** Outer ring of a spherical roller bearing  
**Symptom:** Wear having a wavy or concave-and-convex texture on loaded side of raceway surface  
**Cause:** Entry of debris under repeated vibration while stationary



**Photo 7-10-3**  
**Part:** Inner ring of a double-row tapered roller bearing  
**Symptom:** Fretting wear of raceway and stepped wear on the rib face  
**Cause:** Fretting progression due to excessive load while stationary



**Photo 7-10-4**  
**Part:** Tapered rollers of Photo 7-10-3  
**Symptom:** Stepped wear on the roller head and face  
**Cause:** Fretting progression due to excessive load while stationary

### 7.11 Fretting

Damage Condition	Possible Cause	Measures
Wear occurs due to repeated sliding between the two surfaces. Fretting occurs at fitting surface and also at contact area between raceway ring and rolling elements. Fretting corrosion is another term used to describe the reddish brown or black worn particles.	Poor lubrication Vibration with a small amplitude Insufficient interference	<ul style="list-style-type: none"> <li>• Use a proper lubricant</li> <li>• Apply a preload</li> <li>• Check the interference fit</li> <li>• Apply a film of lubricant to the fitting surface</li> </ul>

### 7.12 False Brinelling

Damage Condition	Possible Cause	Measures
Among the different types of fretting, false brinelling is the occurrence of hollow spots that resemble brinell dents, and are due to wear caused by vibration and swaying at the contact points between the rolling elements and raceway.	Oscillation and vibration of a stationary bearing during such times as transporting Oscillating motion with a small amplitude Poor lubrication	<ul style="list-style-type: none"> <li>• Secure the shaft and housing during transporting</li> <li>• Transport with the inner and outer rings packed separately</li> <li>• Reduce the vibration by preloading</li> <li>• Use a proper lubricant</li> </ul>



**Photo 7-11-1**  
**Part:** Inner ring of a deep groove ball bearing  
**Symptom:** Fretting occurs on the bore surface  
**Cause:** Vibration



**Photo 7-11-2**  
**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Notable fretting occurs over entire circumference of bore surface  
**Cause:** Insufficient interference fit



**Photo 7-12-1**  
**Part:** Inner ring of a deep groove ball bearing  
**Symptom:** False brinelling occurs on the raceway  
**Cause:** Vibration from an external source while stationary



**Photo 7-12-2**  
**Part:** Outer ring of Photo 7-12-1  
**Symptom:** False brinelling occurs on the raceway  
**Cause:** Vibration from an external source while stationary



**Photo 7-11-3**  
**Part:** Outer ring of a double-row cylindrical roller bearing  
**Symptom:** Fretting occurs on the raceway surface at roller pitch intervals



**Photo 7-12-3**  
**Part:** Outer ring of a thrust ball bearing  
**Symptom:** False brinelling of raceway surface at ball pitch  
**Cause:** Repeated vibration with a small oscillating angle



**Photo 7-12-4**  
**Part:** Rollers of a cylindrical roller bearing  
**Symptom:** False brinelling occurs on rolling surface  
**Cause:** Vibration from an external source while stationary

### 7.13 Creep

Damage Condition	Possible Cause	Measures
Creep is the phenomenon in bearings where relative slipping occurs at the fitting surfaces and thereby creates a clearance at the fitting surface. Creep causes a shiny appearance, occasionally with scoring or wear.	Insufficient interference or loose fit Insufficient sleeve tightening	<ul style="list-style-type: none"> <li>• Check the interference, and prevent rotation</li> <li>• Correct the sleeve tightening</li> <li>• Study the shaft and housing precision</li> <li>• Preload in the axial direction</li> <li>• Tighten the raceway ring side face</li> <li>• Apply adhesive to the fitting surface</li> <li>• Apply a film of lubricant to the fitting surface</li> </ul>



**Photo 7-13-1**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Creep accompanied by scoring of bore surface  
**Cause:** Insufficient interference



**Photo 7-13-2**  
**Part:** Outer ring of a spherical roller bearing  
**Symptom:** Creep occurs over entire circumference of outside surface  
**Cause:** Loose fit between outer ring and housing

### 7.14 Seizure

Damage Condition	Possible Cause	Measures
When sudden overheating occurs during rotation, the bearing becomes discolored. Next, raceway rings, rolling elements, and cage will soften, melt and deform as damage accumulates.	Poor lubrication Excessive load (Excessive preload) Excessive rotational speed Excessively small internal clearance Entry of water and debris Poor precision of shaft and housing, excessive shaft bending	<ul style="list-style-type: none"> <li>• Study the lubricant and lubrication method</li> <li>• Reinvestigate the suitability of the bearing type selected</li> <li>• Study the preload, bearing clearance, and fitting</li> <li>• Improve the sealing mechanism</li> <li>• Check the precision of the shaft and housing</li> <li>• Improve the mounting method</li> </ul>



**Photo 7-14-1**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Raceway is discolored and melted. Worn particles from the cage were rolled and attached to the raceway  
**Cause:** Insufficient lubrication



**Photo 7-14-2**  
**Part:** Convex rollers of Photo 7-14-1  
**Symptom:** Discoloration and melting of roller rolling surface, adhesion of worn particles from cage  
**Cause:** Insufficient lubrication



**Photo 7-14-3**  
**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Raceway discoloration, melting occurs at ball pitch intervals  
**Cause:** Excessive preload



**Photo 7-14-4**  
**Part:** Outer ring in Photo 7-14-3  
**Symptom:** Raceway discoloration, melting occurs at ball pitch intervals  
**Cause:** Excessive preload




**Photo 7-14-5**  
**Part:** Balls and cage of Photo 7-14-3  
**Symptom:** Cage is damaged by melting, balls become discolored and melted  
**Cause:** Excessive preload



### 7.15 Electrical Corrosion

Damage Condition	Possible Cause	Measures
When electric current passes through a bearing, arcing and burning occur through the thin oil film at points of contact between the race and rolling elements. The points of contact are melted locally to form "fluting" or groove-like corrugations which are seen by the naked eye. The magnification of these grooves will reveal crater-like depressions which indicate melting by arcing.	Electrical potential difference between inner and outer rings Electrical potential difference of a high frequency that is generated by instruments or substrates when used near a bearing.	<ul style="list-style-type: none"> <li>• Design electric circuits which prevent current flow through the bearings</li> <li>• Insulation of the bearing</li> </ul>



**Photo 7-15-1**  
**Part:** Inner ring of a tapered roller bearing  
**Symptom:** Striped pattern of corrosion occurs on the raceway surface




**Photo 7-15-2**  
**Part:** Tapered rollers in Photo 7-15-1  
**Symptom:** Striped pattern of corrosion occurs on the rolling surface



**Photo 7-15-3**  
**Part:** Inner ring of a cylindrical roller bearing  
**Symptom:** Belt pattern of electrical corrosion accompanied by pits on the raceway surface



**Photo 7-15-4**  
**Part:** Balls of a groove ball bearing  
**Symptom:** Electrical corrosion has a dark color that covers the entire ball surface



**Photo 7-15-5**  
**Part:** Inner ring of a deep groove ball bearing  
**Symptom:** Fluting occurs on the raceway surface (High frequency)



**Photo 7-15-6**  
**Part:** Outer ring of a deep groove ball bearing  
**Symptom:** Fluting occurs on the raceway surface (High frequency)

### 7.16 Rust and Corrosion


Damage Condition	Possible Cause	Measures
Bearing rust and corrosion are pits on the surface of rings and rolling elements and may occur at the rolling element pitch on the rings or over the entire bearing surfaces.	Entry of corrosive gas or water Improper lubricant Formation of water droplets due to condensation of moisture High temperature and high humidity while stationary Poor rust preventive treatment during transporting Improper storage conditions Improper handling	<ul style="list-style-type: none"> <li>• Improve the sealing mechanism</li> <li>• Study the lubrication method</li> <li>• Anti-rust treatment for periods of non-running</li> <li>• Improve the storage methods</li> <li>• Improve the handling method</li> </ul>



**Photo 7-16-1**  
**Part:** Outer ring of a cylindrical roller bearing  
**Symptom:** Rust on the rib face and raceway surface  
**Cause:** Poor lubrication due to water entry



**Photo 7-16-2**  
**Part:** Outer ring of a slewing ring  
**Symptom:** Rust on raceway surface at ball pitch  
**Cause:** Moisture condensation during stationary periods



**Photo 7-16-3**  
**Part:** Inner ring of a spherical roller bearing  
**Symptom:** Rust on raceway surface at roller pitch  
**Cause:** Entry of water into lubricant



**Photo 7-16-4**  
**Part:** Rollers of a spherical roller bearing  
**Symptom:** Pit-shaped rust on rolling contact surface, Corroded portions.  
**Cause:** Moisture condensation during storage

### 7.17 Mounting Flaws

Damage Condition	Possible Cause	Measures
Straight line scratches on surface of raceways or rolling elements caused during mounting or dismounting of bearing.	Inclination of inner and outer rings during mounting or dismounting. Shock load during mounting or dismounting.	<ul style="list-style-type: none"> <li>• Use appropriate jig and tool</li> <li>• Avoid a shock load by use of a press machine</li> <li>• Center the relative mating parts during mounting</li> </ul>



**Photo 7-17-1**  
**Part:** Inner ring of a cylindrical roller bearing  
**Symptom:** Axial scratches on raceway surface  
**Cause:** Inclination of inner and outer rings during mounting




**Photo 7-17-2**  
**Part:** Outer ring of a double-row cylindrical roller bearing  
**Symptom:** Axial scratches at roller pitch intervals on raceway surface  
**Cause:** Inclination of inner and outer rings during mounting




**Photo 7-17-3**  
**Part:** Rollers of a cylindrical roller bearing  
**Symptom:** Axial scratches on rolling surface  
**Cause:** Inclination of inner and outer rings during mounting

### 7.18 Discoloration

Damage Condition	Possible Cause	Measure
Discoloration of cage, rolling elements, and raceway ring occurs due to a reaction with lubricant and high temperature.	Poor lubrication Oil stain due to a reaction with lubricant High temperature	<ul style="list-style-type: none"> <li>• Improve the lubrication method</li> </ul>



**Photo 7-18-1**  
**Part:** Inner ring of an angular contact ball bearing  
**Symptom:** Bluish or purplish discoloration on raceway surface  
**Cause:** Heat generation due to poor lubrication



**Photo 7-18-2**  
**Part:** Inner ring of a 4-point contact ball bearing  
**Symptom:** Bluish or purplish discoloration on raceway surface  
**Cause:** Heat generation due to poor lubrication



## Appendix Bearing Diagnostic Chart

Damage name	Location (Phenomenon)	Cause											Remarks					
		Handling		Bearing surrounding			Lubrication		Load		Speed							
		Stock/Shipping	Mounting	Shaft Housing	Sealed device	Water/Debris	Temperature	Lubricant	Lubrication method	Excessive load	Impact load	Moment		Ultra small load	High speed, High acceleration & deceleration	Shaking/Vibration	Stationary	Bearing Selection
1. Flaking	Raceway, Rolling surface																	
2. Peeling	Raceway, Rolling surface																	
	Bearing outside surface (Rolling contact)			*														* Mating rolling part
3. Scoring	Roller end face surface, Rib surface																	
	Cage guide surface, Pocket surface																	
4. Smearing	Raceway, Rolling surface																	
5. Fracture	Raceway collar, Rollers																	
6. Cracks	Raceway rings, Rolling elements																	
	Rib surface, Roller end face, Cage guide surface (Thermal crack)																	
7. Cage damage	(Deformation), (Fracture)																	
	(Wear)																	
8. Denting	Raceway, Rolling surface, (Innumerable small dents)																	
	Raceway (Debris on the rolling element pitch)																	
9. Pitting	Raceway, Rolling surface																	
10. Wear	Raceway, Rolling surface, Rib surface, Roller end face																	
11. Fretting	Raceway, Rolling surface																	
	Bearing outside & bore, side surface (Contact with housing and shaft)																	
12. False brinelling	Raceway, Rolling surface																	
13. Creep	Fitting surface																	* Clearance fit
14. Seizure	Raceway ring, Rolling element, Cage																	
15. Electrical corrosion	Raceway, Rolling surface			*	*													* Electricity passing through the rolling element
16. Rust and corrosion	Raceway ring, Rolling element, Cage																	
17. Mounting flaws	Raceway, Rolling surface																	
18. Discoloration	Raceway ring, Rolling element, Cage																	

**Remark:** This chart is not comprehensive. It lists only the more commonly occurring damages, causes, and locations.

MEMO

---

# PRODUCT TABLE

## Ball Bearings

**O.D. up to 1900 mm**

RADIAL	Single Row Deep Groove Ball Bearings		Single Row Angular Contact Ball Bearings	
	Single Row Paired Angular Contact Ball Bearings		Double Row Angular Contact Ball Bearings	

**O.D. up to 1925 mm**

**O.D. up to 1600 mm**

AXIAL	Single Direction Thrust Ball Bearings		Double Direction Thrust Ball Bearings	
-------	---------------------------------------	--	---------------------------------------	--

## Spherical Roller Bearings

**O.D. up to 1580 mm**

RADIAL	Spherical Roller Bearings	
	Toroidal Roller Bearings	

**O.D. up to 1400 mm**

AXIAL	Spherical Roller Thrust Bearings	
-------	----------------------------------	--

## Other Products

**O.D. up to 400 mm**

RADIAL	Track and Needle Roller Bearings	
	Special and Split Roller Bearings	

**O.D. up to 1800 mm**

AXIAL	Slewing Bearings	
-------	------------------	--

### Notes


1. Bearing dimensional and running accuracy according to ISO/AFBMA/GOST standards
2. All bearings available in metric and inch sizes, with cylindrical or tapered bore
3. Special features available on request

# PRODUCT TABLE

## Cylindrical Roller Bearings


O.D. up to 1800 mm

Single Row Cylindrical Roller Bearings




O.D. up to 1800 mm

Double Row Cylindrical Roller Bearings




O.D. up to 1400 mm

Multi Row Cylindrical Roller Bearings




O.D. up to 1600 mm

Single Direction Cylindrical Roller Thrust Bearings



Double Direction Cylindrical Roller Thrust Bearings




RADIAL

CYLINDRICAL ROLLERS

## Tapered Roller Bearings

O.D. up to 1800 mm


Single Row Tapered Roller Bearings



Single Row Paired Tapered Roller Bearings


O.D. up to 1925 mm

Double Row Tapered Roller Bearings




O.D. up to 1925 mm

Multi Row Tapered Roller Bearings




O.D. up to 1600 mm

Single Direction Tapered Roller Thrust Bearings



O.D. up to 1600 mm

Double Direction Tapered Roller Thrust Bearings



RADIAL

TAPERED ROLLERS

AXIAL



**FV BEARING INDUSTRIES**

Add: Chuangzhan-Building, Nanchang Road, Jianxi Industry Zone,  
Luoyang City, Henan Province, P.R.C.

Tel: +86-379-62901536 Fax: +86-379-63621986  
Mail: [service@fv-bearing.com](mailto:service@fv-bearing.com) Web: [www.fv-bearing.com](http://www.fv-bearing.com)